

# Cement Repair Express

Revision: 16/07/2019

Page 1 from 2

## Technical data

|                                 |                    |
|---------------------------------|--------------------|
| Basis                           | Acrylic dispersion |
| Consistency                     | Paste              |
| Curing system                   | Physical drying    |
| Skin formation* (23°C/50% R.H.) | Ca. 30 min         |
| Density                         | Ca. 1,67 g/ml      |
| Temperature resistance**        | -20 °C → 80 °C     |
| Application temperature         | 5 °C → 30 °C       |
| Shrinkage                       | Shrink free        |

\* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. \*\* This information relates to fully cured product.

## Product description

Cement Repair Express is a high quality filler with granular structure for easy and shrink free repairing of cracks and joints in concrete.

## Properties

- Very good adhesion to many mineral surfaces in indoor and outdoor applications.
- Very fast curing
- Does not shrink
- Paintable (after a few hours depending on the amount of material applied)

## Applications

- For repairing holes and cracks in concrete and cement
- For the repairing of joints in brickwork
- Repairing of damage in eg. concrete stairs.

## Packaging

Colour: cement grey

Packaging: 300 ml cartridge

## Shelf life

At least 12 months in unopened packaging in a dry storage place at temperatures between +5 °C and +25 °C. Protect against frost.

## Substrates

Substrates: all common porous surfaces in construction and renovation. Not suitable for bituminous materials, glass, metal, PE, PTFE

and PP.

Nature: the substrates to be sealed must be clean, dry and free of dust.

Surface preparation: Highly porous surfaces should be primed with diluted Cement Repair Express ( 1 part Cement Repair Express + 2 parts water).

We recommend a preliminary adhesion test on every surface.

## Joint dimensions

Static joints up to 5 cm.

## Application method

Application method: Remove any loose particles before applying Cement Repair Express. Apply the sealant with a caulking gun or putty knife into the joint or crack. Finishing with a wet spatula or trowel gives the smoothest result. For large cracks, static joints or large screw holes apply preferably 2 layers of the product. Depending on the porosity of the substrate, apply the second layer of product after ca. 30 min.

Cleaning: Before curing, Cement Repair Express can be removed with water from substrates and tools.

Finishing: with wet putty knife or trowel

Repair: With the same material.

## Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult the packaging label for more information.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

---

## Cement Repair Express

---

Revision: 16/07/2019

Page 2 from 2

**Remarks**

- Do not use in applications where continuous water immersion is possible.
- Not suitable for expansion and dilatation joints.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.