

# Soudafoam Gap Filler Click and Fix

Revision: 15/07/2021

Page 1 from 2

## Technical data

Basis	Polyurethane
Consistency	Stable foam, thixotropic
Curing system	Moisture curing
Skin Formation (EN 17333-3)	10 min
Cutting Time (EN 17333-3)	25 min
Free foamed density (EN 17333-1)	Ca. 27 kg/m <sup>3</sup>
Sound insulation (EN ISO 717-1)	58 dB
Box Yield (EN 17333-1)	750 ml yields ca. 28 l of foam
Joint Yield (EN 17333-1)	750 ml yields ca. 22 m of foam
Shrinkage after curing (EN 17333-2)	< 2 %
Expansion after curing (EN 17333-2)	None
Compressive strength (EN 17333-4)	Ca. 21 kPa
Shear strength (EN 17333-4)	Ca. 33 kPa
Tensile Strength (EN 17333-4)	Ca. 79 kPa
Elongation at Fmax (EN 17333-4)	Ca. 11 %
Temperature resistance**	-40 °C till +90 °C (cured)

\*\* This information relates to fully cured product.

## Product description

Soudafoam Gap Filler Click and Fix is a one-component, self-expanding, ready to use polyurethane foam. It has been fitted with the unique patented Click&Fix adaptor system for maximum comfort during application.

Soudafoam Gap Filler Click and Fix is filled with HCFC- and CFC-free propellants which are not harmful for the ozon layer. Because of the Duravalve, the optimal yield remains over the entire shelf life, even when stored or transported lying down.

## Properties

- Excellent stability (no shrinkage or post-expansion)
- High filling capacity
- Good adhesion on all surfaces (except PE, PP and PTFE).
- High insulation value, thermal and acoustic
- Very good bonding properties.
- Not UV-resistant
- Freon free (not harmless to ozone layer and greenhouse effect)
- Click and Fix system for maximum comfort in use

## Applications

- Installing of window and door frames.
- Filling of cavities.
- Sealing of all openings in roof constructions.
- Apply of an acoustic baffle
- Improving thermal isolation in cooling systems.

## Packaging

*Colour:* champagne

*Packaging:* 750 ml aerosol (net)

## Shelf life

24 months unopened and stored in dry and cool conditions (Between 5 and 25 °C), Upright storage is recommended.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

---

## Soudafoam Gap Filler Click and Fix

---

Revision: 15/07/2021

Page 2 from 2

### Application method

Shake the aerosol can for at least 20 seconds. Fit the gun on the adapter. Surface should be free from grease and dust. Moisten surfaces with a water sprayer prior to application. For non-conventional substrates a preliminary adhesion test is recommended. Fill holes and cavities for 65 %, as the foam will expand. Repeat shaking regularly during application. If you have to work in layers repeat moistening after each layer. Fresh foam can be removed using Soudal Gun & Foamcleaner or acetone. Prior to using the Gun & Foamcleaner, test whether surfaces are affected or not. Especially plastics and lacquer or paint layers can be sensitive to this. Cured foam can only be removed mechanically or with Soudal PU-Remover.

Can temperature: +5 °C - 30 °C

Ambient temperature: +5 °C - 30 °C.

Surface temperature: +5 °C - 35 °C

### Health- and Safety Recommendations

Take the usual labour hygiene into account. Always wear gloves and goggles. Remove cured foam mechanically. Never burn away. Consult label and material safety data sheet for more information. When vaporizing (for example with a compressor), additional security measures will be required. Use only in well ventilated areas.

### Remarks

- Moisten surfaces with a water sprayer prior to application. If you have to work in layers repeat moistening after each layer. For not common surfaces we recommend an adhesion test.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.