

Painters Caulk Express

Revision: 18/10/2022

Page 1 from 2

Technical data

Basis	Acrylic dispersion
Consistency	Paste
Curing system	Physical drying
Skin formation* (23°C/50% R.H.)	Ca. 20 min
Density	Ca. 1,70 g/ml
Temperature resistance**	-20 °C → 80 °C
Application temperature	5 °C → 30 °C
Shrinkage	Ca. 15% (DIN 52451)

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

Painters Caulk Express is a high quality, plasto-elastic one-component, acrylic joint sealant for interior applications. Due to a fast curing Painters Caulk Express is faster paintable.

Properties

- Very easy to apply
- Colourfast and waterproof after curing
- Paintable after 10 minutes
- Very good adhesion on many porous surfaces and aluminium

Applications

- Sealant for cracks in concrete and plaster work.
- Connection joints in building industry.
- Joints on window sills, between plinths and walls, between masonry, ...

Packaging

Colour: white, grey, brown, black
Packaging: 80 ml tube, 300 ml cartridge, 600 ml foil bag

Shelf life

At least 12 months in unopened packaging in a dry storage place at temperatures between +5 °C and +25 °C. Protect against frost.

Substrates

Substrates: all common porous surfaces in construction and renovation. Not suitable for natural stone, bitumen, glass and metal.

Nature: the substrates to be sealed must be clean, dry and free of dust.

Surface preparation: Highly porous surfaces should be primed with diluted Painters Caulk Express (1 part Painters Caulk Express + 2 parts water).

We recommend a preliminary adhesion test on every surface.

Joint dimensions

Min. width for joints: 5 mm

Max. width for joints: 20 mm

Min. depth for joints: 5 mm

Recommendation sealing jobs: joint width = joint depth. Use PE backer rods before applying the sealant in large joints to avoid 3-point adhesion.

Application method

Application method: Apply the sealant by means of a manual or pneumatic caulking gun into the joint. Next finish with for example a filling-knife.

Do not apply when rain or frost is imminent during curing process.

Cleaning: Before curing, Painters Caulk Express can be removed with water from substrates and tools.

Finishing: Finish with a spatula or putty knife.

Repair: With the same material.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Painters Caulk Express

Revision: 18/10/2022

Page 2 from 2

Health- and Safety Recommendations

Take the usual labour hygiene into account.
Consult the label for more information.

Remarks

- Do not use in applications where continuous water immersion is possible.
- Paintable with most paints.
- The paint must be sufficiently elastic to allow application on a plasto-elastic sealant.
- Given the great diversity in available paints it is recommended to do a compatibility test prior to application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.