



Silirub MPS

Product description

Silirub MPS is a high quality, elastic one-component joint sealant based on silicone.

Properties

- Very good adhesion on many materials
- Easy to apply
- Good UV resistance
- Impervious to mold.
- Permanently elastic after curing
- Typical acetic smell
- Not paintable
- Not suitable for natural stone

Applications

- Connection joints between wall and bathtubs or shower bases.
- Interior applications which are exposed to high relative humidity
- Sealing joints in sanitary rooms (bathroom) and kitchens.

Technical data

Base		Polysiloxane
Consistency		Stable paste
Curing system		Moisture curing
Skin formation		Ca. 20 min
Curing speed		Ca. 2 mm/24h
Density		Ca. 0.95 g/ml
Maximum allowed distortion		± 25 %
Elasticity modulus	ISO 37	Ca. 0.23 N/mm ²
Elongation at break	ISO 37	Ca. 800 %
Maximum tension	ISO 37	Ca. 1.45 N/mm ²
Hardness		15 ± 5 Shore A
Application temperature		+5°C → +35°C
Temperature resistance		-60°C → +120°C

Footnote: Skinning time and curing speed may vary depending on environmental factors such as temperature, moisture, and type of substrates.

Substrates

- Substrate condition
The surface must be rigid, clean, dry, free of dust and grease.
- Substrate preparation
Porous surfaces should be primed with Primer 150. If needed non porous surfaces can be prepared with a Soudal activator or cleaner (see Technical Data Sheet).



Silirub MPS

■ Substrate types

Silirub MPS has a good adhesion to following substrates: all usual building substrates, etc.. Silirub MPS has no good adhesion or is not suitable for PE, PP, PTFE (Teflon®), PVC, concrete, bituminous substrates. We recommend a preliminary adhesion and compatibility test on every surface.

Application method

■ Application method

Apply the product by means of a manual-, battery- or pneumatic- caulking gun. Apply the product evenly without air inclusions into the joint. Smoothen the joint with a spatula with the help of finishing solution. Avoid that finishing solution comes between the joint edges and sealant (to prevent adhesion loss). It is important to ventilate well the places where the product is applied. Continue to ventilate throughout the curing time.

■ Cleaning method

Clean with Soudal Surface Cleaner or with Soudal Swipex Wipes, immediately after use.

■ Finishing method

With Soudal Finishing Solution before skinning.

■ Repair method

Repair with the same material.

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult the packaging label and safety data sheet for more information.

Use only in well-ventilated areas.

Keep the area well ventilated during use and curing of the product.

Dangerous. Respect the precautions for use.

Packaging/Logistics

Colour: Please consult the product catalogue, the Soudal website or a Soudal representative.

Packaging: Please consult the product catalogue, the Soudal website or a Soudal representative.

Shelf life: 12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Joint dimensions

■ Min. width for joints: 5 mm

Max. width for joints: 30 mm

Min. depth for joints: 5 mm

Recommendation for sealing jobs: joint width = 2 x joint depth

Environmental clauses

■ Leed regulation: Silirub MPS conforms to the requirements of LEED. Low -Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Remarks

■ Because of the acid nature, certain metals (eg copper, lead) can be affected.

■ Do not use on natural stones like marble, granite,...(staining).

■ Direct contact with the secondary sealing of insulating glass units (insulation) and the PVB-film of safety glass must be avoided.

■ A total absence of UV can cause a color change of the sealant.

■ In an acid environment or in a dark room, a white sealant can slightly turn yellow. Under the influence of sunlight it will turn back to its initial colour.

■ When finishing with a finishing- or soapy solution, make sure that the surfaces are not touched by this solution. This will cause the sealant not to adhere to that surface. Therefore we recommend to only dip the finishing tool in this solution.

■ We strongly recommend not to apply the Finishing Solution in full sunlight as it will dry very fast in these circumstances.

■ Do not use on polycarbonate



Silirub MPS

- Not suitable for bonding aquariums.
- Do not use in applications where continuous water immersion is possible.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.

This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. It is general in nature and does not constitute any liability. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application. In every case it is recommended to carry out preliminary experiments. The manufacturer reserves the right to modify products without prior notice.